



GP zones (dark spots) in the matrix of an Al-15Ag alloy dissolving near plates of the more stable precipitates (dark lines). Transmission electron micrograph of a specimen aged 1,200 h at 160°C (320°F). 23,000 \times . Source: J.R. Davis, Ed., *Aluminum and Aluminum Alloys*, *ASM Specialty Handbook*, ASM International, 1993, p 291